

INSTRUCCIONES DE TRABAJO

Versión nº: 2 Fecha de revisión: Septiembre 2011
IDT-605: Fichas técnicas de producto

**TECHNICAL DATA****LOOP F.R.T.****Características de construcción**

Construcción
 Composición básica
 Acabado

Ancho : < 50 mm
 ≥ 50 mm
 ≥ 100 mm

Espesor

Peso

Características de empleo

Pelaje con cierre HOOK*

Cizallamiento con cierre HOOK*

Vida del cierre *

Carga de rotura *

Encogimiento al lavado (3 x 60°C)*

Solidez color al frotamiento ISO 105 sec/X12
 Solidez color al agua ISO 105 sec/EO1
 Solidez color al agua de mar ISO 105 sec/EO2
 Solidez color a la luz ISO 105 sec /BO2

Solidez color al sudor ISO 105 sec/EO4

Comportamiento al fuego (Norma F.A.R. 25853)

Longitud quemada
 Tiempo de auto-extinción
 Tiempo de auto-extinción del goteo

* Norma interna VESA

Tejido
 Poliamida
 Poliuretano F.R.T.

Nominal ± 1 mm
 Nominal ± 1.5 mm
 Nominal ± 2 mm

2.35 ± 0.25 mm

300 g/m² ± 10 %

Promedio 2.0 N/cm
 Mínimo 1.3 N/cm

Promedio 10.3 N/cm²
 Mínimo 7.3 N/cm²

Pérdida del 50 % después de 5000 aberturas

Mínimo 210 N/cm

Máximo 4%

4 mínimo
 4 mínimo
 4 mínimo
 5 mínimo (colores oscuros)
 4 mínimo (blanco y colores claros)
 4 mínimo

≤ 200 mm
 ≤ 15 segundos
 ≤ 5 segundos

Las indicaciones contenidas en esta hoja de información están basadas en pruebas y ensayos fidedignos. Valor promedio como referencia únicamente, no especificación nominal. Dada la diversidad de usos de nuestros productos, aconsejamos a nuestros clientes se aseguren que el producto cumple con la utilización deseada, asumiendo en este caso responsabilidad de su uso.

Elaborado: J.C. Lima

Revisado: E. Ducet

Autorizado: J. Jacobs

Fecha: 27.09.11

ANEXO: IDT – 605-A

FTP 201 Versión 3

INSTRUCCIONES DE TRABAJO

Versión nº: 2 Fecha de revisión: Septiembre 2011
IDT-605: Fichas técnicas de producto



TECHNICAL DATA

LOOP F.R.T.

Construction characteristics

Basic construction
 Base material
 Standard binder backing

Width : < 50 mm
 ≥ 50 mm
 ≥ 100 mm

Overall thickness

Weight

Usage characteristics

Peel Strength with Hook std *

Shear Strength with Hook std *

Cycle life *

Breaking Strength *

Shrinkage after washing (3 x 60°C) *

Colourfastness to rubbing ISO 105 sec/X12
 Colourfastness to water ISO 105 sec/EO1
 Colourfastness to sea water ISO 105 sec/EO2
 Colourfastness to light ISO 105 sec/BO2

Colourfastness to perspiration ISO 105 sec/EO4

Flammability test according F.A.R. 25853

Burn length
 Combined after flame and glow time
 Flaming time of drips

* Internal norm of VESA

Woven
 Polyamide
 Polyurethane F.R.T.

Nominal ± 1 mm
 Nominal ± 1.5 mm
 Nominal ± 2 mm

2.35 ± 0.25 mm

300 g/m² ± 10 %

Average 2.0 N/cm
 Minimum 1.3 N/cm

Average 10.3 N/cm²
 Minimum 7.3 N/cm²

50 % loss after 5000 cycles

Minimum 210 N/cm

Maximum 4 %

4 minimum
 4 minimum
 4 minimum
 5 minimum (dark colours)
 4 minimum (white and light colours)
 4 minimum

≤ 200 mm
 ≤ 15 seconds
 ≤ 5 seconds

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

Elaborado: J.C. Lima

Revisado: E. Ducet

Autorizado: J. Jacobs

Fecha: 27.09.11

ANEXO: IDT – 605-B

FTP 201 Versión 3